

Adsorption of Analytes Occurs Rapidly in Autosampler Vials – Tips & Suggestions

Date: 1-MAY-2020 Last Updated: 15-JANUARY-2026

Rapid Adsorption of Basic Analytes in Autosampler Vials :

A Hidden Variable in Sample Integrity

Adsorption to borosilicate glass surfaces is time-dependent—but can occur rapidly. Our previous studies have demonstrated that certain analytes can experience significant concentration loss due to surface adsorption in autosampler vials, even within minutes of sample preparation. This phenomenon poses a risk to data integrity, particularly in trace-level quantification.

Experimental Insight

In a controlled experiment, we monitored 5 ppm cetylpyridinium chloride over short time intervals to assess adsorption behavior. Two vial types were compared:

- A market-leading “Certified” Type-33 borosilicate glass vial
- An RSA™ (Reduced Surface Activity) vial designed to minimize surface interactions

Key Findings


- In the standard Type-33 glass vial, a notable decrease in peak area was observed within just 15 minutes post-preparation, indicating rapid analyte loss due to adsorption.
- In contrast, the RSA™ vial maintained consistent peak area, demonstrating superior surface inertness and analyte recovery.

Implications for the Lab

- Even short autosampler queue times can introduce variability in quantitation.
- Surface activity of vial materials should be considered a critical parameter in method development and validation—especially for analytes prone to adsorption.

Recommendation: For sensitive or adsorption-prone compounds, use RSA™ or similarly low-activity vials to preserve sample integrity and reproducibility.

In the chromatograms below, you can observe significant peak area diminishing in the standard HPLC vials (*left*), in just a matter of fifteen minutes from the immediate prep and analysis, versus the peak area in RSA™ Vials (*Right*).



Printed from the Chrom Resource Center
Copyright 2025, All Rights Apply
MicroSolv Technology Corporation
9158 Industrial Blvd. NE, Leland, NC 28451

Tel: (732) 380-8900
Fax: (910) 769-9435
Email: customers@mtc-usa.com
Website: www.mtc-usa.com